



Product Data Sheet

Santa Fe

DESCRIPTION

Santa Fe is a 100% pure acrylic based, quartz enhanced product designed for use over properly installed and prepared FC sheeting, polystyrene building systems and where a flat, lightly textured appearance and long lasting, flexible finish is desired. *Santa Fe* is supplied ready to use in 15 litre pails,

Colours

Santa Fe can be factory tinted to a wide range of commercially available light to mid strength colours to create a 'patinaed' finish.

ADVANTAGES

Santa Fe provides:-

- Excellent adhesion to all correctly prepared substrates.
- A tough, knock resistant surface that is perfect for over coating with RSA 955 *Impact* paint or *Clear Coat*.
- Excellent flexibility - overcoming shrinkage and minor cracking associated with cement renders.
- A long lasting high integrity finish suitable for both interior and exterior use.
- A non tacky, easy to apply formulation.
- An extended 'hang time' helping the plasterer to provide a seamless finish.
- An ideal stone size which offers an excellent guide for even application.
- Less wear and tear on shoulders and more square metres finished per day, because the product is easy to float finish.

TYPICAL USES

Santa Fe is typically used over properly prepared FC sheeting, EP rendered expanded polystyrene, AAC (Hebel), tilt panel concrete and rendered masonry. *Santa Fe* can also be used over properly prepared pre-painted

surfaces where a 'low build' finish (1-3mm) is required.

SUITABLE SUBSTRATES

When applied in accordance with the most recent RSA written information, *Santa Fe* is suitable for use over all correctly prepared substrates including:-

- Acrylic and cement based renders
- Bricks, blocks and AAC (Hebel)
- Slab edge, off-form and tilt panel concrete
- Painted surfaces
- Fibre cement sheeting and plasterboard
- Expanded polystyrene paneling and blocks

THEORETICAL COVERAGE

When applied as a tight coat one 15 litre bucket will cover approximately 12-14m².

Note: The theoretical coverage is based on a true flat substrate that has no recesses or voids with minimum suction (porosity) and depends on application techniques.

APPLICATION AND THICKNESS

Santa Fe is applied by steel trowel in thicknesses from 1mm-2mm per coat.

Subsequent coats can be applied to build the depth up to 6mm if required.

When applied as a tight coat (approximately 1mm thick) and plastic floated a look similar to the RSA sample will be achieved.

Note: The theoretical coverage is based on a true flat substrate that has no recesses or voids with minimum suction (porosity) and depends on application techniques.

FINISHING

Santa Fe is finished using a plastic float.

Santa Fe Product Data Sheet

WORKMANSHIP STANDARDS

When correctly applied in accordance with RSA substrate preparation and product application information, *Santa Fe* will offer a high quality, natural, seamless finish.

DRYING

Allow 24 hours drying time per 1mm of applied *Santa Fe* (based on conditions at 25°C and 55% relative humidity).

CLEAN UP

Clean all tools and equipment with water.

OVER-COATING

Prior to the application of RSA paints such as *955 Impact* or *Clear Coat*, the *Santa Fe* and its substrate must contain less than 15% Wood Moisture Equivalent (WME). **Note: Should the *Santa Fe* have a moisture content of more than 15% WME the 955 paint film could blister and peel and the *Clear Coat* may maintain a 'milky/cloudy' look.**

IMPORTANT PREPARATION AND APPLICATION NOTES

(For more information refer to the relevant application, substrate and general information sheets)

- All site mix and non RSA sand and cement based renders must be allowed to cure for 28 days and contain less than 15% WME prior to application of RSA primer and then *Santa Fe*.
- It is absolutely critical to correctly prime site mix and non RSA sand and cement renders using *Grit Primer AE*.
- Preparation of substrates, application of *Santa Fe* and clean up processes must be in accordance with the latest RSA written information (refer to the relevant application and substrate coating information sheets).
- Batch to batch colour variations will occur due to the use of natural sand in the product. Correct mixing and batching must be adhered to (see *RSA Working with Coloured Products* information sheet).

- Control/expansion/movement joints in all substrates must be carried through the trowel-on coating system to a minimum width of 10mm.
- The product cannot be expected to straighten substrates, hide major imperfections, or remedy poor quality substrate installations.
- The product is not a substitute for good solid plastering trade practices. It is the plasterer's responsibility to assess each project to determine 'best practice'. If in doubt phone 07 3287 6444.
- Protect freshly applied product from rain, high winds, freezing and temperatures below 5°C for 48 hours after application.
- Product should only be applied within a temperature range of 5-35°C.
- Do not use in areas subject to continual damp or fully submerged substrates.

HEALTH AND SAFETY

Please consult the **Material Safety Data Sheet** and read the product packaging carefully before use. Material Safety Data Sheets are available by phoning **07 3287 6444** or **1800 077 744**.

Please Note:- The information given in this data sheet is based on our current knowledge of the product when properly stored, handled and applied. We cannot guarantee that the product will be suitable, effective or safe when used for any purpose other than its stated uses. To the extent that it is lawful, we exclude warranties implied by law and limit our liability to the cost of replacing the product. We accept no responsibility for loss or injury caused by improper use, incompetent preparation, inexperienced or negligent application, or ordinary wear and tear. Service or advice given by our staff should not amount to responsibility for the project - since the owner, or their contractor (and not River Sands), is responsible for procedures relating to the application of the product.



Render Systems Australia
A Division of River Sands Pty Ltd
683 Beenleigh-Redland Bay Rd
Carbrook 4130
Ph:- 07 3287 6444 Fax:- 07 3287 6445

Service Centres
Geebung Ph:- 07 3865 6888
Nerang Ph:- 07 5596 2399
Sunshine Coast Ph:- 07 5438 8900
Toll Free: Ph:- 1800 077 744
www.render systems australia.com.au